


Copper Sheet & Plate


Roll Copper - Standard Roofing Sizes



■ Temper 060 (Soft)

Weight per Sq Ft		Thickness	Gauge	Size	Lbs/Lin Ft	Temper	Part Number
Ozs.	Lbs/Sq Ft						
16	1.000	.0216	24	6 x COIL	.500	Soft	142828
16	1.000	.0216	24	8 x COIL	.670	Soft	142836
16	1.000	.0216	24	10 x COIL	.830	Soft	142844
16	1.000	.0216	24	12 x COIL	1.000	Soft	241842
16	1.000	.0216	24	14 x COIL	1.170	Soft	142860
16	1.000	.0216	24	16 x COIL	1.330	Soft	142878
16	1.000	.0216	24	20 x COIL	1.670	Soft	142886

Roll Copper - Non-Standard Roofing Sizes



- UNS Designation Number: UNS C11000 ETP
- Nominal Chemicals: Copper 99.9%, Oxygen .04%
- Average Physical Properties:
 - Temper: Soft
 - Tensile: 34,000 psi
 - Hardness: F50
- Electrical Conductivity: 101% IACS
- Specifications: ASTM B 370, Temper (1/8 Hard)

Electro-Deposited, Soft Temper, ANSI/IPC-MF-150F

Weight per Sq Ft	Lbs/ sq Ft	Thickness	Size	Part Number
1/2 oz.	.032	.00070	25 x COIL	544266
1 oz.	.063	.00135	25 x COIL	294316
3 oz.	.188	.00405	25 x COIL	294332
5 oz.	.068	.00675	25 x COIL	294340

Copper in Coils, Rolled, Soft Temper, ASTM B 370

Weight per Sq Ft	Lbs/ sq Ft	Thickness	Size	Part Number
	.231	.005	12 x COIL	142894
	.300	.006	12 RDM x COIL	558370
	.300	.005	24 x COIL	560961
8 oz.	.500	.0108	12 x COIL	508294
8 oz.	.500	.0108	30 x COIL	142925

Dimensions are in inches. All weights are approximate.
 Sizes not shown may be available upon request.